



EAGLE FONDA FIX RAPID-SET FOUNDATION REPAIR CONCRETE

Description

Eagle Fonda Fix is a fast setting concrete, polymer-modified that repair defects of 6 mm (1/4") to 75 mm (3") thick in one application. This concrete is specially formulated for the conditioning of work inside or outside concrete as the horizontal and vertical. This is excellent to level and make a nice finish on concrete walls.

Surface Preparation

Surface preparation: Avoid working in bright sunlight. The surface must be sound, clean and free from dust, oil, grease, wax, paint or other materials that may interfere with adhesion.

Application

Mixture: Mix only the amount that can be applied in 10 to 15 minutes In a container, pour 170 ml of water per kilogram of product gradually adding the powder Eagle Fonda Fix. Mix at low speed with a drill and a paint shaker for 1 to 2 minutes, paddling sides of the container and stirrer to obtain a homogeneous mixture. Proceed immediately to the application and finishing.

Drying

Eagle Fonda Fix takes less than 30 minutes to dry. Temperature and humidity can make vary the drying time. Protect the surface from rain. If you use a polythene avoid contact with the surface that could damage the finish.

Cleanning

Clean working tools and hands with water while product is still fresh

Package

This product is available in 5 kg, 10kg and 22,7 kg.

Shelf Life

Store in a cool, dry place. Shelflife is 12 months in original unopened containers.





EAGLE FONDA FIX RAPID-SET FOUNDATION REPAIR CONCRETE

Tecnnical date table

CARACTERISTICS	CURE	EAGLE FONDA FIX (17% water)
Pot life		12 minutes
Open time		15 minutes / 35 minutes
Density ASTM C-185		1.88 kg/l
Compressive strength ASTM C -109	3 hours	12 MPa (1740 PSI)
	24 hours	14 MPa (2030 PSI)
	7 days	29 MPa (4206 PSI)
	28 days	35 MPa (5076 PSI)
Flexural strength ASTM C-348	24 hours	6.5 MPa (943 PSI)
	7 days	10.0 MPa (1450 PSI)
	28 days	10.9 MPa (1580 PSI)
Pull-out strength on concrete CSA A23.2-6B	7 days	1.85 MPa (268 PSI)
	28 days	2.13 MPa (309 PSI)
Coverage per Kg of product		0.09 m ² to 6 mm thickness (1 ft ² à 1/4 in thickness)

*Dry time dependent of surface porosity and temperature.

Garantie

The customer shall verify of the suitability of this product for the intended purpose. Applicator's skill, weather and surface conditions being beyond manufacturer's control, we limit our liability to replacement of defective material only in sealed container, within 1 year of proof of purchase. FOB plant.

CORROSIVE : This product contains a cementitious blend and lime and may cause eyes, skin and respiratory system irritation.

When using this product : Wear safety glasses, gloves and a NIOSH approved anti-dust mask.

FIRST AID TREATMENT : **Skin contact** : Wash with soap and water. **Eye contact** : Flush eyes immediately and abundantly with water for 15 minutes keeping eyelids opened. Consult a physician immediately. **Ingestion** : DO NOT INDUCE VOMITING. Give water if conscious. Keep victim warm and call immediately a physician.

KEEP OUT OF REACH OF CHILDREN.

READ SAFETY DATA SHEET BEFORE USING THIS PRODUCT

